## **Product List:**



## Flexible (Open Cell) Foam Casting Resin Systems

Page 1 of 1

Product Code	Free Rise Density (LBS/ft3)	Compressed Density (LBS/ft3)	Mixing Ratio (by weight)	Mixing Ration (by volume)	Pot life	Demolding Time	General Description
MPA-F03A	3.3	3.6	100: 179	100: 214	10 Sec.	30 min.	Open cell flexible foam for cushioning products. Variable ratio to fine-tune the foam consistency. Water blown foam.
MPP-F04C	4.2	4.6	100: 122	75: 100	30 Sec.	35 min.	Open cell flexible foam for cushioning products. Relatively long pot life for manual processing. Variable ratio to fine-tune the foam consistency.  Water blown foam.
<u>MPP-F07B</u>	6.5	7.3	100: 100	100: 106	60 Sec.	2 hours	Open cell flexible foam for cushioning products and gap filling. Relatively long pot life for manual processing. Variable ratio to fine-tune the foam consistency. Water blown foam.
<u>FFM-1</u>	8.5	9.3	100: 86	100: 100	20 Sec.	40 min.	Very firm flexible foam. Bumper parts. Archery Targets. Piplinee cleaner (P.I.G.) parts. Long enough pot life to make small parts manually.
<u>VEF-152</u>	7.5	8.2	100: 260	100: 300	25 Sec.	45 min.	Viscoelastic foam for specialty foam cushion products. Long enough pot life for making small parts by manual process. Variable ratio to fine tune the foam consistency

Tandem Products, Inc. / DBA Northstar Polymers 3444 Cheatham Avenue, Minneapolis, MN 55406 USA

Tel: (612)721-2911

Email: info@northstarpolymers.com

Notice: All of the statements, recommendations, suggestions, and data concerning the subject material are based on our laboratory results, and although we believe the same to be reliable, we expressly do not represent, warrant, or guarantee the accuracy, completeness, or reliability of same, or the material or the results to be obtained from the use thereof, neither do we warrant that any such use, either alone or in combination with other materials, shall be free of the rightful claim of any third party by way of INFRINGEMENT or the like, and TANDEM PRODUCTS and NORTHSTAR POLYMERS DISCLAIMS ALL WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE