

# Product List:



## Structural (Rigid) Foam Casting Resin Systems

Product Code	Free Rise Density (LBS/ft3)	Copressed Density (LBS/ft3)	Mixing Ratio (by weight)	Mixing Ration (by volume)	Pot life	Demolding Time	General Description
<a href="#"><u>MPA-M02B</u></a>	2.2	2.4	100:86	100:100	15 Sec.	5 min.	Semi-rigid light foam for packaging foam, making light/large items, foam die for machining, creating temporary barriers, filling large space.
<a href="#"><u>MPP-R04B</u></a>	4.0	4.5	100:86	100:100	40 Sec.	60 min.	Closed cell structural cell foam for making light parts and filling gaps. Relatively long pot life enable a small amount to be manually cast in place.
<a href="#"><u>MPP-R07B</u></a>	6.4	7.0	100: 86	100:100	40 Sec.	30 min.	Closed cell structural foam for making light/stronger parts. Filling space for protecting sensitive parts. Relatively long pot life enable a small amount to be manually cast in place.

**Tandem Products, Inc. / DBA Northstar Polymers**  
 3444 Cheatham Avenue, Minneapolis, MN 55406 USA

Tel: (612)721-2911  
 Email: [info@northstarpolymers.com](mailto:info@northstarpolymers.com)

Notice: All of the statements, recommendations, suggestions, and data concerning the subject material are based on our laboratory results, and although we believe the same to be reliable, we expressly do not represent, warrant, or guarantee the accuracy, completeness, or reliability of same, or the material or the results to be obtained from the use thereof, neither do we warrant that any such use, either alone or in combination with other materials, shall be free of the rightful claim of any third party by way of INFRINGEMENT or the like, and TANDEM PRODUCTS and NORTHSTAR POLYMERS DISCLAIMS ALL WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY and FITNESS FOR A