

GK-7R4

Polyurethane Gel Casting System for “Sticky Sheets/Pads” Applications

GK-7R4 is specifically formulated for manufacturing “sticky sheets” or “sticky pads” with the 2-part resin casting process. The material can be processed at room temperature and can be manually processed to make smaller production quantities to make “pressure sensitive adhesive” (PSA) products.

Unlike typical PSA tapes, this formula makes reusable sticky pad products. The cured material is intrinsically sticky without use of tackifier resin. Film made of GK-7R4 retains sticky surface indefinitely. When the surface is contaminated with dust and oil, it can easily be washed with soap and water to regain the stickiness. The cured film is soft and flexible but very strong to resist cut and tear.



Unlike other PSA tape products, GK-7R4 can be made to have a sticky surface that does not leave residue on substrate surface. The stickiness can be adjusted by simply adjusting the mixing ratio between the given part-A/part-B components so that the processors can fine-tune the stickiness of their products without formula modification.

Possible applications for GK-7R4 include cell-phone holders for dash boards, multipurpose sticky pads, lint remover film, sticky guitar pick holder and muting pads for other instruments, temporary adhesives for apparels and other consumer products, and many other custom applications.

Please also refer to “FAQ for Making “Sticky Pads” or Polyurethane Based PSA Products” in later pages in this document for more information.

Designations

System Code:	GK-7R4
Part-A:	MPG-028 (Prepolymer)
Part-B:	PPA-163 (Curative)



Northstar Polymers (Div. of Tandem Products, Inc.)
3444 Dight Avenue South, Minneapolis, MN 55406 USA
Tel: (612)721-2911, Email: info@northstarpolymers.com

Mixing Ratios:

Suggested Starting Point Mixing Ratio:

1: 7.8 by Weight
1: 8.3 by Volume
12: 100 gear pump ratio

This formulation is made in such a way that a user can change the stickiness of the material by adjusting the mixing ratio. The stickiness changes from various processing parameters such as temperature, thickness, and substrate material. We suggest starting at 1: 7.8 = part-A: part-B ratio using your set up, and then adjust the ratio if the stickiness is not within the ideal range for your application. A higher part-B ratio makes a stickier product, and a lower part-B ratio makes a less sticky product. You can test it in the increments of 2 to 3% by weight of part-B to see the changes. Increasing part-B ratio makes softer and stickier products with less cohesion strength.

Processing Temperature:

Part-A: Ambient
Part-B: Ambient
Mold: Ambient

Pot-life: 8 - 10 minutes (at the starting point ratio)
Demolding Time: 2 - 6 hours (at the starting point ratio)
Complete Cure: 3 - 4 days at room temperature
(The curing pattern can be modification by use of heat and catalyst variation.)

Component Properties

Part-A: MPG-028

General Description: Isocyanate Prepolymer
NCO: 14.9%
Equivalent Weight: 282
Specific Gravity: 1.113 grams/cm³
Viscosity (@72 °F): 1,900 cps

Storage/Handling: Store indoor at room temperature between 72 °F and 86 °F all time. The container headspace must be purged to blanket the material with dry nitrogen gas or argon gas.





Northstar Polymers (Div. of Tandem Products, Inc.)
 3444 Dight Avenue South, Minneapolis, MN 55406 USA
 Tel: (612)721-2911, Email: info@northstarpolymers.com

MPG-028 is also sensitive to cold temperature. During cold seasons, the material may freeze during transportation. If freezing is suspected, please heat the material, immediately after receiving, to about 140 °F or until the entire content is clear smooth liquid with yellow tint. Keeping MPG-028 frozen for a long time will ruin the material.

Part-B: PPA-163 (Curative)

General Description: Curing Agent/ Curative/ Polyol Blend
 Equivalent Weight: 1630
 Specific Gravity (at 77 °F): 1.048 grams/cm³
 Viscosity (at 77 °F): 900 cps

Storage/Handling: Store indoor at room temperature between 72 and 86 °F in airtight containers. Avoid moisture entering the product.

Typical Physical Properties of Cured Sheet

GK-7R4 is a variable ratio formulation. By changing the mixing ratio between the given part-A and part-B components, the user can change the adhesion strength. The physical properties of the resulted product also change. The following chart shows the typical physical properties of GK-7R4 made at different mixing ratios.

	Mix Ratio (Part-A: Part-B by weight)	Adhesion Strength to PET (LBS of force)	Hardness (Shore OO Durometer)	Tensile Strength (psi)	Elongation
#1	1:7.34	2.5	45-50	57.3	>1000%
#2	1:7.74	2.9	40-45	36.2	>1000%
#3	1:8.14	3.9	25-30	10.8	>1000%

The adhesion property of the material is also affected by the processing conditions. The above data is based on our lab tests and reference only. The Adhesion Strength is measured with our in-house method. The data values are expressed in the maximum pounds of force to delaminate 1" x 2" piece of GK-7R4 off from PET film with an in-house 90-degree separation method. The tensile strength, as well as elongation values, are also tested in our in-house tensile/elongation test method. #2 yields the starting point stickiness, which is close to the majority of sticky pad products in the market.

For Stronger Adhesion Strength

GK-7R4 services the typical stickiness range of common sticky pad applications. For stronger adhesion requirements, we recommend using another one of our formulations for reusable PSA applications, GK-22R. GK-22R yields sticky pad products with higher adhesion strength. Please refer to the Technical Data Sheet for GK-22R for more information.





Northstar Polymers (Div. of Tandem Products, Inc.)
3444 Dight Avenue South, Minneapolis, MN 55406 USA
Tel: (612)721-2911, Email: info@northstarpolymers.com

Packaging Sizes:

- 5-gallon pails (40 LBS per pail)
- 55-gallon drums (450 LBS per drum)

FAQ for Making “Sticky Pads” or Polyurethane Based PSA Products

What are the advantages of polyurethane gel sticky pads and PSA products?

Polyurethane gel is intrinsically sticky and very soft polymer. Other materials used in PSA applications are often some polymers with liquid additive called “tackifier”, which create the sticky surface. Polyurethane gel formulas we supply are 2-part casting resin materials, which can make thicker sheets and pads instead of creating thin coat of sticky layer on films or paper substrates. The surface of sticky polyurethane gel can be washable with soap and water when it is contaminated by dust/oil to recover the stickiness. The processor can control the stickiness so that he/she can make the end product with right stickiness that does not leave residue on the applied surfaces. The soft elastomeric quality of the material itself cushions and dampens impact as well as vibrations when used shock/vibration mitigation products.

What is the difference between other sticky-tape products and polyurethane gel sticky pads?

Surfaces of typical polyurethane gel elastomers are intrinsically sticky. If you slice a piece of polyurethane gel sticky pad in half, the cut surface is also sticky. The cured material is sticky not only on the surface, but inside of pad is also sticky.

Unlike other PSA products made of other types of polymers such as acrylates, vinyl, and rubber based coatings on web, polyurethane gel can be sticky without use of a liquid tackifier (plasticizer) additive. Many other PSA products (such as sticky tapes, labels, and stickers) are made with solid polymer blended with liquid tackifier to coat the surfaces of paper or plastic film. The liquid part of this sticky coating on regular sticky tape products can leach out from the polymer body of coating. This may leave some residue on applied surfaces. As the liquid additive leaves the polymer, the tack property of tape may change.

Polyurethane gel sticky pad does not have to use liquid additive to create the stickiness. This is because polyurethane gel is formulated in such a way the cured polymer itself takes a state between solid and liquid, which we call “gel” state.

In general, the coating layers of common sticky tapes are thin, and those PSA products are often not reusable after it is applied once, because this thin sticky layer can either be absorbed into the applied surface or contaminated from particles from the applied surface. Once it is contaminated, typically you cannot use water to wash off because it washes of the sticky layer together with the contaminants.





Northstar Polymers (Div. of Tandem Products, Inc.)
3444 Dight Avenue South, Minneapolis, MN 55406 USA
Tel: (612)721-2911, Email: info@northstarpolymers.com

Polyurethane gel is two-part casting resin. This enables the user to make sticky pads with much thicker layer, it is unlikely to lose sticky surface to substrate. The surface is washable without losing stickiness.

Can polyurethane gel sticky pads stick to everything?

Polyurethane gel can be made into products with a wide range of stickiness. It can be made to stick to many things. However, how a sticky pad sticks to different surfaces will be all different depending on the surface. Sticky pads (and all other PSA products such as commonly available sticky tapes) adhere to different surfaces with different adhesion strengths. The most important quality in the surfaces is the “surface energy” of the substrate.

Each material has its unique surface energy level. In general, sticky pads and other PSA products are easier to adhere to surfaces with higher surface energy. For example, glass surfaces have high surface energy. So, sticky pads will stick with higher adhesion strength.

Solid silicone polymer has very low surface energy, so the sticky pads do not adhere to solid silicone.

Plastics, wall paints, and other polymer surfaces have different surface energy levels. For example, PET and polycarbonate have high surface energy, so sticky pads stick strongly. Polypropylene, polyethylene, and latex rubber have low surface energy, and sticky pads don't stick to those very well.

Polyurethane gel sticky pads can be made to stick to a wide range of different materials, but it cannot create one sticky pad with exactly the same sticking strength to different materials of different surface energy levels. When you design your product, you must limit the applicable material surfaces so you can expect the adhesion strength of your sticky pad is within the expected level. Once you have the target surfaces, you then need to adjust the stickiness by adjusting the mixing ratio between part-A and par-B components to make sticky pads to test for the adhesion strengths on those surfaces.

I want to attach the sticky pads to another part. Can I use glue on cured sticky pads to permanently adhere to other parts?

This will be difficult because cured polyurethane gel has low surface energy. It will not create a good permanent adhesion with glue. In this situation, you need to make a laminate of sticky material on high-surface-energy plastic film material.

Typically, PET films are used to make these laminates. You can simply cast a blend of metered part-A/part-B components on to the PET film and cure. This will make a permanent adhesion between the sticky layer and PET film. The open side of PET film can be used to adhere to other surfaces using commonly available glue products (such as Superglue) to create permanent adhesion. Some PET film products contain an internal release agent, which prevents layers of film from sticking to each other. If you need to use such a film, you may need to use a surface modification method to increase the surface energy of the film.

Can I use polyurethane gel sticky material for medical or personal care applications?





Northstar Polymers (Div. of Tandem Products, Inc.)
3444 Dight Avenue South, Minneapolis, MN 55406 USA
Tel: (612)721-2911, Email: info@northstarpolymers.com

If you need to confirm skin contact safety or the cytotoxicity of the material for your application, you should not use polyurethane gel. We use industrial-grade raw materials, which contain a small amount of impurities. Even a very small amount of impurities, such as residual catalysts, additives, and monomers may become an issue for certain applications with strict regulatory conformances and safety concerns.

More questions?

Please feel free to contact us at info@northstarpolymers.com to ask any questions regarding the content of this document.

Storage, Handling, Safety Information

Storage:

Part-A component (prepolymer) contains isocyanate component, which is very much sensitive to moisture. If it is left in air, part-A will react with atmospheric moisture and will be ruined. This reaction is non-reversible. Soon after opening a can and dispensing the content, nitrogen gas or negative-40-degree-due-point dry air needs to be injected to the can to blanket the material. Silica gel or calcium chloride desiccant filter should be installed to 55-gallon drum-vent for your drum feeding system. The storage temperature should be at a room temperature between 72 and 87 °F.

Part-A component freezes just below room temperature. The material may be frozen when you receive. Part-A component must be thawed immediately. If the material is left frozen for an extended period of time, a side reaction undergoes, and the material will be ruined. The material temperature needs to reach 140 °F to be thawed. Please consult the instructions provided by Northstar Polymers for details. If a large amount of water mixes with a large amount of isocyanate base materials, the chemical reaction may produce a large amount of CO₂ gas and heat to create a hazardous condition. Keep the storage area free of water.

Under a certain combination of heat, catalyst (basic chemicals), amounts of reactive materials, and some other favorable conditions for the reaction, the water (or alcohol/glycol/amine) to isocyanate reaction can reach a dangerous state of accelerated reaction. The accelerated reaction may create a very high temperature condition. The thermal decomposition of isocyanate-based materials by extremely high temperature or fire can produce toxic gasses and smokes. Please be sure that the containers are stored in dry indoor storage, away from source of large amount of water.

If a leak is found in a drum, please place the drum in such a position that the leaking part is at the highest part of drum so that the content no longer leaks out. Cover the leaking area with dry towel to prevent air from entering. If possible, transfer the material into new container(s) with nitrogen purge. If moisture enters into an isocyanate container from a small leakage, CO₂ gas may be produced to gradually pressurize the container. If pressure built up is suspected, open the bung (or cap) very slowly to release the pressure before you change the drum position.

Part-B component is hygroscopic. If the material is exposed to ambient air, it may absorb moisture. Moisture contaminated part-B material may become source of degradation or excessive bubbles in the product. Avoid exposure of the material to air. Purging the empty space in the container with nitrogen gas or negative-40-degree-due-point dry air is also recommended to prevent moisture contamination of part-B as well; however, most of the





Northstar Polymers (Div. of Tandem Products, Inc.)
3444 Dight Avenue South, Minneapolis, MN 55406 USA
Tel: (612)721-2911, Email: info@northstarpolymers.com

cases, keeping in an airtight container will be sufficient. Store it in a dry indoor storage at a room temperature between 65 and 85 °F. The moisture contamination of part-B material is reversible. By heating material to 160 - 180 °F and vacuuming it at about 29" Hg negative pressure for several hours will reduce the moisture level.

Safety Information:

The component materials are industrial-grade chemicals. Please keep them in a secure place and prevent access from any unauthorized individual. The personnel who handle these materials need to read the Safety Data Sheet (SDS) for detail information on safety and handling of the material. The SDS for each component is sent with the shipment of the material.

When using this material, be sure to operate in a wide-open area with good air movement, or in a well-ventilated area. Wear rubber gloves, long sleeves, and protective eyeglasses to prevent skin/eye contact of the material. When your operation involves heating or spraying of the material, and if you expect the isocyanate content level in the work place atmosphere may become above the threshold regulated by OSHA or by other appropriate working place safety standard, we recommend, in addition to the above, installation of a proper hooded dynamic ventilation system and/or using an appropriate type of respirator (such as a full-face respirator equipped with OSHA approved HEPA filters for particulate and organic vapor) to prevent inhalation of the fume.

Direct contact of polyurethane raw materials to skin/eye, as well as ingestion may lead to health problems. No eating or smoking should be permitted at the working area. The operator should wash hands well with soap and water after handling the materials and follow the other procedures of the Standard Industrial Hygiene Practices. Please refer to the MSDS for each component for the detailed health information.

For any questions, please contact Northstar Polymers.

Tel: 612-721-2911.
Fax: 612-721-1009
Web Site: <http://www.northstarpolymers.com>
E-Mail: info@northstarpolymers.com

Tel: 612-721-2911.
Fax: 612-721-1009
Web Site: <http://www.northstarpolymers.com>
E-Mail: info@northstarpolymers.com

Notice: All of the statements, recommendations, suggestions, and data concerning the subject material are based on our laboratory results, and although we believe the same to be reliable, we expressly do not represent, warrant, or guarantee the accuracy, completeness, or reliability of same, or the material or the results to be obtained from the use thereof, neither do we warrant that any such use, either alone or in combination with other materials, shall be free of the rightful claim of any third party by way of INFRINGEMENT or the like, and NORTHSTAR POLYMERS DISCLAIMS ALL WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE.

Revision: 1/26/2022

