



Northstar Polymers (Div. of Tandem Products, Inc.)  
3444 Dight Avenue South, Minneapolis, MN 55406 USA  
Tel: (612)721-2911, Email: info@northstarpolymers.com

## MPP-D45B

### Technical Data Sheet

MPP-D45B is polyether based polyurethane casting resin formulation for a variety of custom applications. The cured material has a good physical strength for this class of material with hardness of 95A to 45D Durometer for a good load bearing capacity with flexibility. The component materials are liquid at room temperature and can be processed without use of auxiliary heating in low-cost molds. Relatively low viscosity of raw material components allows easy mix and good mold resolution. This set of properties makes MPP-D45B an excellent choice for making aftermarket bushings, impact pads, prototyping, short-run productions, and many other applications.

#### Typical Physical Property:

Hardness  
Tensile  
Elongation  
Die-C Tear  
Split Tear  
Bashore Rebound  
Natural Color:

#### Lab Test Data

45D Durometer  
1898 psi  
196%  
407 pli  
94 pli  
21%  
Off-white to Yellow Opaque

#### Designations

System Code: MPP-D45B  
Part-A (Isocyanate) Component: MPB-025  
Part-B (Curative) Component: PBB-016

#### Ratio Information

Mixing Ratio: 1: 0.667 = Part-A: Part-B by volume (60:40 Gear Ratio)  
1: 0.604 = Part-A: Part-B by Weight  
NCO Index: 1.018

#### Processing Temperature

Part-A: Ambient 72 - 82 °F  
Part-B: Ambient 72 - 82 °F  
Mold Temperature: Ambient 72 - 82 °F

#### Curing Pattern

Pot-Life: 5-7 minutes  
Demolding Time: 60 minutes (plastic mold, 1/2" thickness sample)





Northstar Polymers (Div. of Tandem Products, Inc.)  
3444 Dight Avenue South, Minneapolis, MN 55406 USA  
Tel: (612)721-2911, Email: info@northstarpolymers.com

Post-Cure (Recommended): 3 to 6 hours at 180 °F  
Complete Cure: 3 days at room temperature

### Component Materials (Typical Properties)

#### **Part-A: MPB-025 (Isocyanate)**

General Description: Isocyanate Terminated Prepolymer based on MDI and polyether polyol  
NCO: 17.0%  
Equivalent Weight: 247  
Specific Gravity (Theoretical at 77 °F): 1.131 grams/cm<sup>3</sup>  
Viscosity: 450 cps at 72 °F

Storage/Handling: Store indoor at room temperature between 72 Ambient 72 - 82 °F and 105 °F. The ideal storage temperature is 90 °F. The container head space must be purged to blanket the material with dry nitrogen gas or argon gas.

#### **Part-B: PBB-016 (Curative)**

General Description: Curing Agent (Curative) based on polyether polyol, extender, and additives  
Equivalent Weight: 152  
Specific Gravity (Theoretical at 77 °F): 1.042 grams/cm<sup>3</sup>  
Viscosity: 900 cps at 77 °F

Storage/Handling: Store indoor at room temperature between 72 and 105 °F. Avoid moisture entering the product. The constituents tend to separate in container. Be sure to agitate the content before dispensing out of the container each time.

#### Standard Packages:

5-gallon pails (40 pounds per pail)  
55-gallon drums (450 pounds per drum)

### Storage/Handling Information for the Component Materials

#### Storage:

##### Part-A (Isocyanate Prepolymer) Component

Part-A component (prepolymer) contains isocyanate component, which is highly sensitive to moisture. If it is left in air, part-A will react with atmospheric moisture and will be ruined. This reaction is non-reversible. Soon after opening the container to dispense the content, dry nitrogen gas or argon gas needs to be injected to the





Northstar Polymers (Div. of Tandem Products, Inc.)  
3444 Dight Avenue South, Minneapolis, MN 55406 USA  
Tel: (612)721-2911, Email: info@northstarpolymers.com

container to purge and blanket the top space. Please consult Northstar Polymers for nitrogen gas set-up information.

For gravity feeding system from a 55-gallon, silica gel or calcium chloride desiccant filter(s) should be installed to the vent-hole of the drum. A valve to inject dry nitrogen gas can be installed instead.

During transportation, there is a chance of freezing. The frozen material must be immediately thawed to avoid permanent damage from freezing. If the material color is opaque with the consistency of thick liquid, gel, waxy, or solid, the material requires immediate thawing. The container should be put into an industrial oven at 180 °F until the material temperature is 140 °F or the color of the material is clear with smooth liquid consistency. Storing frozen material at above 35 °F for more than a few days will cause a permanent damage to the material, and it will not be returnable or refundable.

Store the containers a dry indoor storage within the temperature range between 85 and 105 °F. Avoid direct sunlight.

If a large amount of water mixes with a large amount of isocyanate base materials, the chemical reaction may produce a large amount of CO<sub>2</sub> gas and heat to create a hazardous condition. Keep the storage area free of water.

Under a certain combination of heat, catalyst (basic chemicals), amounts of reactive materials, and some other favorable conditions for the reaction, the water (or alcohol/glycol/amine) to isocyanate reaction can reach a dangerous state of accelerated reaction. The accelerated reaction may create a very high temperature condition. The thermal decomposition of isocyanate based material by extremely high temperature or fire can produce toxic gasses and smokes. Please be sure that the containers are stored in dry indoor storage, away from source of large amount of water.

If a leak is found in a drum, please place the drum in such a position that the leaking part is at the highest part of drum so that the content no longer leaks out. Cover the leaking area with dry towel to prevent air from entering. If possible, transfer the material into new container(s) with nitrogen purge. If moisture enters into an isocyanate container from a small leakage, CO<sub>2</sub> gas may be produced to gradually pressurize the container. If pressure built up is suspected, open the bung (or cap) very slowly to release the pressure before you change the drum position.

#### Part-B (Curative) Component

Part-B component is hygroscopic. If the material is exposed to ambient air, it absorbs moisture. Part-B component contaminated by moisture can become a source excessive bubbles in the product after mixed with part-A. Avoid exposure of the material to moisture in air.

Purging the empty space in the container with dry nitrogen gas, argon gas, or negative-40-degree-due-point dry air is also recommended to prevent moisture contamination of part-B as well. (However, simply keeping the material in an airtight container may also be sufficient depending on the moisture level of the work place.)

Store it in a dry indoor storage at a room temperature between 72 and 90 °F. Avoid direct sunlight.

Note: Moisture contamination of part-B material can be reversed by heating material to 180 °F and vacuuming it at about 29" Hg or above negative pressure for 20 to 40 minutes.





Northstar Polymers (Div. of Tandem Products, Inc.)  
3444 Dight Avenue South, Minneapolis, MN 55406 USA  
Tel: (612)721-2911, Email: [info@northstarpolymers.com](mailto:info@northstarpolymers.com)

Part-B material contains chemical constituents that can separate during the storage. Agitation of the part-B content before dispensing may be required for the system. Separation can be seen in a higher degree when the material is stored in cold temperature. You may need to heat to re-blend the separated material in some cases. Please consult Northstar Polymers when separation is suspected.

**Safety:**

The component materials are industrial-grade chemicals. Please keep them in a secure place and prevent access from any unauthorized individual. The personnel who handle these materials need to read the Safety Data Sheet (SDS) for detail information on safety and handling of the material. The SDS for each component is sent with the shipment of the material.

When using this material, be sure to operate in a wide-open area with good air movement, or in a well-ventilated area. Wear rubber gloves, long sleeves, and protective eyeglasses to prevent skin/eye contact of the material. When your operation involves heating or spraying of the material, and if you expect the isocyanate content level in the work place atmosphere may become above the threshold regulated by OSHA or by other appropriate working place safety standard, we recommend, in addition to the above, installation of a proper hooded dynamic ventilation system and/or using an appropriate type of respirator (such as a full-face respirator equipped with OSHA approved HEPA filters for particulate and organic vapor) to prevent inhalation of the fume.

Direct contact of polyurethane raw materials to skin/eye, as well as ingestion may lead to health problems. No eating or smoking should be permitted at the working area. The operator should wash hands well with soap and water after handling the materials and follow the other procedures of the Standard Industrial Hygiene Practices. Please refer to the MSDS for each component for the detailed health information.

For any questions, please contact Northstar Polymers.

Tel: 612-721-2911.  
Fax: 612-721-1009  
Web Site: <http://www.northstarpolymers.com>  
E-Mail: [info@northstarpolymers.com](mailto:info@northstarpolymers.com)

**Notice:** All of the statements, recommendations, suggestions, and data concerning the subject material are based on our laboratory results, and although we believe the same to be reliable, we expressly do not represent, warrant, or guarantee the accuracy, completeness, or reliability of same, or the material or the results to be obtained from the use thereof, neither do we warrant that any such use, either alone or in combination with other materials, shall be free of the rightful claim of any third party by way of INFRINGEMENT or the like, and NORTHSTAR POLYMERS DISCLAIMS ALL WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE.

5/30/2019

